



## White Top Kraft Liner – Italy (Food Certified\*)

	127	140	150	161
<b>Grade Code</b>	WT26	WT29	WT31	WT33
<b>Conditioned Basis Wt (7.5%H<sub>2</sub>O)</b> <i>Tappi T 410</i>				
Nominal	127	140	150	161
Reject Above	137	151	161	171
Reject Below	122	137	140	156
<b>Moisture Average, %</b> <i>Tappi T 412</i>				
Average (%)	Mill Specific	Mill Specific	Mill Specific	Mill Specific
Range (+ / -)	1.5	1.5	1.5	1.5
<b>Moisture Variation, %</b> Maximum 2-Sigma (CD)	1.5	1.5	1.5	1.5
<b>Mullen, kPa</b> <i>Tappi T 807</i>				
Reject Below	413	413	413	496
<b>Ring Crush (CD), kN/m</b> <i>Tappi T 822</i>				
Reject Below	--	--	--	--
<b>STFI (CD), Kn/M</b> <i>Tappi T 826</i>				
Reject Below	--	--	2.25	2.55
<b>Porosity (Gurley), sec/100cc</b> <i>Tappi T 460</i>				
Reject Below	15	15	15	15
<b>Internal Bond, N</b> <i>Tappi T 569</i>				
Peel - Reject Below	3.56	3.56	3.56	3.56
<b>Cobb 30 Minute (TOP), gsm</b> <i>Tappi T 441</i>				
Reject Above	155	155	155	155
<b>Smoothness, Sheffield units</b> <i>Tappi T 538</i>				
Sheffield – Reject Above	265	265	310	310
<b>Brightness, %</b> <i>ISO 2469 &amp; 2470</i>				
Average (%)	72.5	72.5	72.5	72.5
Range (+ / -)	2	2	2	2
<b>Caliper, mils</b> <i>Tappi T 411</i>				
Average	Mill specific	Mill specific	Mill specific	Mill specific
Typical CD Roll Variability	+ /- 25.4	+ /- 25.4	+ /- 25.4	+ /- 25.4

\* This quality is certified for direct contact with dry, moist and fatty foodstuffs per the Decreto Ministeriale 21 Marzo 1973, Gazzetta Ufficiale della Repubblica Italiana, 20.4.1973, last modification of 25 September 2007'

888-284-4470

[www.sscboardsales.com](http://www.sscboardsales.com)

Effective Date: July 15, 2008